

UFO

Specification Sheet

CK-30
(MAP-5771-1)

High-Performance Plastic Optical Fiber

E s k a™

MITSUBISHI RAYON CO.,LTD.

Plastic Molding Material Department

1-1, Marunouchi 1-Chome, Chiyoda-ku, Tokyo 100-8253, Japan

Phone :+81-3-6748-7521

Facsimile:+81-3-3286-1384


1. Scope

The specification covers basic requirements for the structure and optical performances of CK-30.

2. Structure

Table 1

		CK-30			
Item		Specification			
		Unit	Min.	Typ.	Max.
Optical Fiber 1	Core Material	—	Polymethyl-Methacrylate Resin		
	Cladding Material	—	Fluorinated Polymer		
	Core Refractive Index	—	1.49		
	Refractive Index Profile	—	Step Index		
	Numerical Aperture	—	0.5		
	Core Diameter	μm	690	735	780
	Cladding Diameter	μm	705	750	795
Approximate Weight		g/m	0.5		

Sectional View

3. Performances

Table 2

CK-30

Item		Acceptance Criterion and/or [Test Condition]	Specification			
			Unit	Min.	Typ.	Max.
Maximum Rating	Storage Temperature	No Physical Deterioration [in a Dry Atmosphere]	°C	-55	—	+70
	Operation Temperature	No Deterioration in Optical Properties* [in a Dry Atmosphere]	°C	-55	—	+70
		No Deterioration in Optical Properties** [under 95%RH condition]	°C	—	—	+60
Optical Properties	Transmission Loss	[650nm Collimated Light] [Standard condition] [10m-1m cutback]	dB/km	—	—	200
Mechanical Characteristics	Minimum Bend Radius	Loss Increment $\leq 0.5\text{dB}$ [A Quarter Bend]	mm	15	—	—
	Tensile Strength	Tensile Force at yield point [in Conformity to the JIS C 6861]	N	32	—	—

All tests are carried out under temperature of 25°C unless otherwise specified.

* Attenuation change shall be within +/- 10% after 1,000 hours.

** Attenuation change shall be within +/- 10% after 1,000 hours, except that due to absorbed water.

4. Revision

REVISION No.	DATE	REMARK	DRAWN	APPVD
	Oct 7, 2011	new issue	Takenaka	Okita
-1	Apr,1,2014	Correction	Takenaka	Okita